



Ateities pl. 40, Kaunas,
Lithuania, LT-52112
tel. 370 37 302 050, 302 057
fax 370 37 302 055
Baltic Pack Group

TECHNICAL DATA SHEET

Brown paper 38 mcr

INFORMATION ON PRODUCT

Greaseproof treated on both sides with kit test 4, wet strength, OBA free.

Suitable for food contact.

Good printability, enduse for bags manufacturing.

Recommended for specialty enduses (for lamination with paper after use of suitable adhesives). It can be used for max 30 min at 220 °C.

TECHNICAL INFORMATION:

<u>Parameters</u>	<u>Unit</u>	<u>Method</u>	<u>Typical value</u>	<u>Tolerances</u>
Substance	g/m²	ISO 536	38	+/- 2
Tensile strenght md	kN/m	ISO 1924-2	3,5	>= 3,1
Tensile strenght cd	kN/m	ISO 1924-2	1,7	>= 1,4
Wet tensile strenght md	kN/m	ISO 3781	0,55	>= 0,45
KIT TEST ws	n°	ISO 16532-2	4	>= 3
KIT TEST fs	n°	ISO 16532-2	4	>= 3
Brightness	%	ISO 2470-2	85	+/- 3
Moisture content	%	ISO 287	6	+/- 1,5

This technical data sheet doesn't release from responsibility to check the suitability of packaging material for the proposed application. The information included in this Technical Data Sheet is based on our experience and actual knowledge and does not imply any responsibility in any way for any subsequential or causal disadvantage or loss.